AMENDMENTS TO THE CLAIMS

1. (currently amended) A polypropylene resin composition which comprises:

a) 40 to 80% by weight of a polypropylene component (A) comprising a copolymer of propylene with ethylene and/or a C_{4-12} α-olefin wherein the amount of units derived from ethylene and/or a C_{4-12} α-olefin is at most 5% by weight ~~or less~~, or a homopolymer of propylene, and

b) 20 to 60% by weight of a copolymer component (B) containing a copolymer (B-1) and a copolymer (B-2),

wherein both the copolymer (B-1) and copolymer (B-2) are copolymers of propylene with ethylene and/or a C_{4-12} α-olefin, in the copolymer (B-1), the amount of units derived from propylene is from more than 50% by weight to 85% by weight, and the copolymer (B-2) is a propylene copolymer where the amount of units derived from propylene is 15 to 50% by weight, the molecular weight distribution (Mw/Mn) by gel permeation chromatography is 3.0 or less, and blockness (CSD) determined using the measured NMR values is 1.3 or less;

in which composition the amount of (B-2) with respect to the whole polypropylene resin composition is at least 3% by weight ~~or more~~, and ~~the~~a ratio of ~~the~~a limiting viscosity of the copolymer (B-1) to ~~the~~a viscosity of the polypropylene component (A), ([η]B-1/[η]A), is at most 1.5 ~~or less~~, and ~~the~~a ratio of ~~the~~a limiting viscosity of the copolymer (B-1) to the viscosity of copolymer (B-2), ([η]B-1/[η]B-2), is at least 0.8 ~~or more~~.

2. (currently amended) The polypropylene resin composition according to claim 1, wherein ~~the~~a weight ratio of the copolymer (B-1) to the copolymer (B-2), [(B-1)/(B-2)], is 1.2 to 6.0.

3. (currently amended) The polypropylene resin composition according to ~~claims 1 and 2~~claim 1, wherein the copolymer (B-2) is a copolymer where there is a heterologous bond, and the ~~unit~~amount of units derived from propylene is 15 to 35% by weight.

4. (currently amended) The polypropylene resin composition according to ~~any of claims 1 to 3~~claim 1, wherein ~~the~~a stereoregularity of the polypropylene component (A) is at least 96% ~~or more~~.

5. (currently amended) A polypropylene resin molding which is prepared by molding ~~the~~a polypropylene resin composition ~~according to any of claims 1 to 4,~~ comprising:

a) 40 to 80% by weight of a polypropylene component (A) comprising a copolymer of propylene with ethylene and/or a C_{4-12} α-olefin wherein the amount of units derived from ethylene and/or a C_{4-12} α-olefin is at most 5% by weight, or a homopolymer of propylene, and

b) 20 to 60% by weight of a copolymer component (B) containing a copolymer (B-1) and a copolymer (B-2),

wherein both the copolymer (B-1) and copolymer (B-2) are copolymers of propylene with ethylene and/or a C_{4-12} α-olefin, in the copolymer (B-1), the amount of units derived from propylene is from more than 50% by weight to 85% by weight, and the copolymer (B-2) is a propylene copolymer where the amount of units derived from propylene is 15 to 50% by weight, the molecular weight distribution (Mw/Mn) by gel permeation chromatography is 3.0 or less, and blockness (CSD) determined using the measured NMR values is 1.3 or less;

in which composition the amount of (B-2) with respect to the whole polypropylene resin composition is at least 3% by weight, and a ratio of a limiting viscosity of the copolymer (B-1) to a viscosity of the polypropylene component (A), ([η]B-1/[η]A), is at most 1.5, and a ratio of a limiting viscosity of the copolymer (B-1) to the viscosity of copolymer (B-2), ([η]B-1/[η]B-2), is at least 0.8.

wherein the copolymer component (B) is dispersed either in layers or as needles in the polypropylene component (A), and ~~the~~an average length (aL) of the dispersed layer is 1.5 μm or longer.

6. (original) The polypropylene resin molding according to claim 6, wherein the molding is a film.